

# IntePro<sup>®</sup> UltraSmooth

IntePro<sup>®</sup> UltraSmooth is manufactured using a patented process that delivers a corrugated polypropylene sheet with a unique surface making it optimal for printing. UltraSmooth offers unmatched print quality, higher output, and lower ink consumption.




## Features & Benefits


- Limits visible grooves or ribs when screen printing
- Standard and custom sheet sizes
- Waterproof
- Recyclable
- Elevates digital printing
- Thickness: 4 mm
- Color: white

## Applications


- In store displays
- Tradeshows and exhibits
- Point of purchase displays
- Premium signage
- Real estate and political signs



Regular corrugated board



IntePro UltraSmooth board





# Specifications

## Width

### Standard Sheet

- $\pm 1/8''$

### Square Cut Sheet

- $-1/16''$  to  $+1/8''$

## Length

### Standard Sheet

- 96": 0" to  $+1''$

### Square Cut Sheet

- 96":  $\pm 1/4''$

## Squareness

(difference between diagonals)

### Length of Standard Sheet

- 96":  $\leq 1/2''$

### Length of Square Cut Sheet

- 96":  $\leq 3/16''$

## Thickness

- $\pm 5\%$

## Surface Treatment

- $> 46$  dyne/cm (4 mm)

## Straightness

### Length of IntePro is 96"

- If the ratio of Length to Width is  $0 \leq 4$ , the Tolerance is  $\leq 3/16''$

## Warp

(highest point of the sheet when place on a flat surface)

### Length of IntePro is 96"

- If the Width is 48", the Tolerance is  $< 3/4''$

## Shipment Quantity

- $-0\%$  to  $+5\%$

# Smoothness Comparison

## TEST 1: Hommel Tester T1000C

	Arithmetical mean roughness	Ten-point mean roughness	Maximum peak
IntePro UltraSmooth	69.29	306.10	373.20
Regular corrugated	298.80	1068.00	1238.00
Surface Superior Rate	431%	349%	332%

## TEST 2: Surface Roughness (Rm)

	A	B	C	D	E
IntePro UltraSmooth	5.4	4.4	5.5	5.4	5.2
Regular corrugated	11.3	11.8	11.1	11.4	11.6
Surface Superior Rate	209%	268%	202%	211%	223%

For patent information, please visit [www.inteplast.com/patents](http://www.inteplast.com/patents)

TEL: 1-800-452-2117 (x1)  
 inteopro@inteplast.com  
 www.inteplast.com

OFFICE: 9 Peach Tree Hill Rd., Livingston, NJ 07039  
 PLANT: 101 Inteplast Blvd., Lolita, TX 77971