Inteplast Group World-Pak Division XF Business Unit

TECHNICAL DATA SHEET

Film Type: XF - GW (Natural Color)

Property	Test Method	Unit	Film	Typical Value		
			Direction			
Unit Weight	XFWI0201	GSM		$70 \pm 10\%$	90 ± 10%	$100 \pm 10\%$
(Nominal Thickness)		Mil		$2.9 \pm 10\%$	$3.8 \pm 10\%$	$4.2 \pm 10\%$
Tensile	ASTM-D882	lb/in	MD/TD avg.	16	19	20
@ Ultimate						
Elongation	ASTM-D882	%	MD/TD avg.	450	475	550
@ Ultimate						
Dart Impact	ASTM-D1709	grams		500	550	600
	(Method A)					
Delamination Strength	Internal	lb/in		1.0	1.0	1.0
Elmendorf Tear	ASTM-D1922	grams	MD/TD avg.	1,200	1,500	1,500
Puncture Propagation Tear	ASTM-D2582	grams	MD/TD avg.	6,000	6,500	7,500

Ref: QCDBMS

The above properties and results obtained refer to the average value of laboratory testing carried out on Inteplast product. These are typical values and intended as guides, not as specification limits. Inteplast urges users to undertake independent testing in order to verify the suitability of the product for their own intended use. Inteplast makes no guarantee of product performance, safety or suitability either expressed or implied, when used alone or in combination with other products. Inteplast disclaims any liability for damages arising from the non-suitability of the product for the effected application.

For additional information, call 1-800-452-2117, extension 8251.

Issued Date: 2/18/19