

**Inteplast Group  
World-Pak Division  
XF Business Unit**

TECHNICAL DATA SHEET

Film Type: XF - US

Property	Test Method	Unit	Film Direction	Typical Value
Unit Weight (Nominal Thickness)	XFWI0201	GSM	--	400 ± 10%
		Mil	--	16.8 ± 10%
Thickness	ASTM D5199	Mil	--	25 ± 10%
Tensile @ Ultimate	ASTM-D882	lb/in	MD/TD avg.	63
Elongation @ Ultimate	ASTM-D882	%	MD/TD avg.	575
Dart Impact	ASTM-D1709 (Method A)	grams	--	2400
Delam Strength	Internal	lb/in	--	1.0
Elmendorf Tear	ASTM-D1922	grams	MD/TD avg.	5,000
Puncture Propagation Tear	ASTM-D2582	grams	MD/TD avg.	18,000
Beach Puncture	ASTM-D781	in-lbs	MD/TD avg.	70

Ref: QCDBMS, LR220802

The above properties and results obtained refer to the average value of laboratory testing carried out on Inteplast product. These are typical values and intended as guides, not as specification limits. Inteplast urges users to undertake independent testing in order to verify the suitability of the product for their own intended use. Inteplast makes no guarantee of product performance, safety or suitability either expressed or implied, when used alone or in combination with other products. Inteplast disclaims any liability for damages arising from the non-suitability of the product for the effected application.

**For additional information, call 1-800-452-2117, extension 8251.**

Issued Date: 8/5/22